

NEXA RESEARCH INSTITUTE

Department of Materials Science & Electrochemistry

Laboratory Notebook

Daily Entry Record

🧪	Experiment ID:	NRI-2024-0047
📅	Date:	14 November 2024
👤	Principal Inv.:	Dr. Elena Marchetti
👥	Team:	James Okonkwo, Priya Nair
📋	Project:	Solid-State Electrolyte Screening

🔒 **Classification:** Internal Confidential | ⚠️ **Hazard Level:** Moderate (H272, H315) | ⚙️ **Version:** 1.0

This entry documents the synthesis and electrochemical characterisation of lithium-garnet composite pellets ($\text{Li}_7\text{La}_3\text{Zr}_2\text{O}_{12}$, LLZO) doped with aluminium. Conductivity measurements at ambient temperature are compared against the baseline undoped batch (NRI-2024-0041) to evaluate the effect of Al^{3+} substitution on ionic transport.

Thursday, 14 November
2024

Session 3 of 5 — Morning

NRI-2024-0047
Experiment Identifier

22.3 °C RH 44 %
Lab environment at 09:07

Researcher

James Okonkwo
Research Associate II
Nexa Research Institute, Lab 4-B
j.okonkwo@nexari.org

Supervisor / Witness

Dr. Elena Marchetti
Principal Investigator
Nexa Research Institute, Lab 4-B
e.marchetti@nexari.org

Objectives & Hypothesis

Primary Objective

Synthesise aluminium-doped LLZO pellets at two dopant concentrations (0.2 mol% and 0.4 mol% Al³⁺) and measure their room-temperature ionic conductivities via electrochemical impedance spectroscopy (EIS) using Au-sputtered blocking electrodes.

Secondary Objectives

- Confirm cubic-phase LLZO formation via X-ray diffraction (XRD) patterns.
- Compare pellet relative densities (target ≥ 94 % of theoretical).
- Record sintering mass loss and attribute to volatile Li₂O evaporation.

Hypothesis

Al³⁺ substitution for Li⁺ at tetrahedral sites will stabilise the cubic garnet phase at room temperature, yielding an ionic conductivity $\sigma \geq 3.0 \times 10^{-4} \text{ S cm}^{-1}$, consistent with the results reported by [1] and the in-house baseline of $\sigma = 1.1 \times 10^{-4} \text{ S cm}^{-1}$ for undoped LLZO batch NRI-2024-0041.

Related protocols: NRI-SOP-EC-07 (EIS procedure), NRI-SOP-SY-12 (solid-state synthesis), NRI-SOP-XR-03 (XRD sample prep).

Materials & Equipment

Reagents

Reagent	Grade	Supplier	Batch No.	Quantity
Li ₂ CO ₃	99.9 %	Apex Chemicals Ltd.	APC-2024-11-07	8.42 g
La ₂ O ₃	99.99 %	Meridian Advanced Mat.	MAM-0943	14.74 g
ZrO ₂	99.5 %	Vertex Inorganics	VTX-ZR-0221	7.36 g
Al ₂ O ₃	99.8 %	Nimbus Labs	NLB-AL-0088	0.34 g
Isopropanol (IPA)	HPLC	Synapse Reagents	SYN-IP-2024	60 mL
Ethanol (abs.)	99.8 %	Synapse Reagents	SYN-ET-2024	20 mL

Equipment

- ✔ High-energy ball mill (Nexa BM-400)

✔ Pellet press, 13 mm die set

✔ Box furnace, max. 1200 °C (NRI-F-02)

✔ Sputter coater (Nimbus SC-10)
- ✔ Potentiostat/galvanostat (Vertex Ivium-V)

✔ XRD diffractometer (Meridian X'Pert3)

✔ Micrometer calliper ($\pm 1\text{ }\mu\text{m}$)

✔ Analytical balance ($\pm 0.01\text{ mg}$)

PPE required: Safety glasses, nitrile gloves, lab coat, dust mask (P2) during powder handling. ⚠ La_2O_3 and Li-compounds are irritants — handle in fume cupboard.

⚙ Procedure

Each step is logged with start time, action, and deviations from the standard operating procedure (NRI-SOP-SY-12).

Step	Time	Stage	Action / Parameters	Deviation / Note
1	09:10	Precursor drying	La_2O_3 dried 12 h at 900 °C; cooled in desiccator. Weighed immediately after.	None.
2	09:35	Stoichiometry calc.	Nominal composition: $\text{Li}_{6.75}\text{Al}_{0.25}\text{La}_3\text{Zr}_2\text{O}_{12}$. Li excess +10 % wt to compensate sintering loss.	Al target 0.2 mol%.
3	09:50	Ball milling	Powders combined in ZrO_2 jars with 60 mL IPA. Milled at 400 rpm, 6 h, 15-min on / 5-min off cycle.	Jar changed after crack found in original jar.
4	16:05	Slurry drying	Slurry transferred to Petri dish; dried at 80 °C, 2 h in convection oven. Powder gently sieved (125 μm mesh).	None.
5	18:20	Pellet pressing	Dried powder uniaxially pressed at 250 MPa; two pellets (P-047-A, P-047-B), 13 mm diameter.	P-047-B cracked on release; discarded.
6	18:45	Calcination	P-047-A placed on MgO setter in box furnace. Ramp 5 °C min ⁻¹ → 1150 °C, dwell 12 h, furnace cool.	Deviation: furnace NRI-F-01 unavailable (maintenance); used NRI-F-02 — calibration verified.
7	Next day	Sintering complete	Retrieved after 14 h cool-down. Mass loss: 3.4 % (expected 3–5 %). Pellet intact, slight opacity.	None.

Raw Observations & Measurements

Pellet physical characterisation (after sintering, before electrodes)

Parameter	P-047-A (0.2 mol% Al)	Target	NRI-2024-0041 (baseline)
Diameter (mm)	12.84	13.00 ± 0.20	12.91
Thickness (mm)	1.37	1.2–1.6	1.41
Mass before sinter (g)	0.9143	—	0.9204
Mass after sinter (g)	0.8832	—	0.8841
Mass loss (%)	3.40	3–5	3.29
Archimedes density (g cm ⁻³)	4.91	≥4.96	4.87
Relative density (%)	92.8	≥94	92.0
Visual appearance	Ivory, slight lustre	—	White-grey

EIS measurement conditions

Temperature: 22.3 ± 0.2 °C
Frequency range: 10⁶ to 10⁻¹ Hz
AC amplitude: 10 mV (rms)
DC bias: 0 V
Electrode material: Au (sputter-coated, 50 nm)
Measurement time: 09:27 – 09:44

Impedance fit results (equivalent circuit: $R_b-CPE_{gb}-CPE_{dl}$):
Bulk resistance R_b : 148.3 Ω
Grain-boundary R_{gb} : 312.7 Ω
 χ^2 goodness of fit: 4.2×10^{-4}
Total resistance R_{tot} : 461.0 Ω
Cell constant ℓ/A : 0.852 cm⁻¹

Derived ionic conductivity

$$\sigma = \frac{\ell}{R_{tot} \cdot A} = \frac{0.852 \text{ cm}^{-1}}{461.0 \text{ } \Omega} = 1.848 \times 10^{-3} \text{ S cm}^{-1}$$

Uncertainty estimate: ±5 % (dominant contributor: Au electrode contact area variability).

Result exceeds hypothesis threshold.

XRD Qualitative Observations (preliminary)

Diffractiongram collected 10° to 70° 2θ at 0.02°/step, 0.5 s/step. Major peaks consistent with cubic garnet space group $Ia\bar{3}d$. No secondary phases (tetragonal LLZO, La₂Zr₂O₇) detectable above noise floor. Rietveld refinement pending (Priya Nair, ETA 16 Nov).

Analysis & Interpretation

Conductivity vs. baseline

The measured total ionic conductivity of P-047-A ($\sigma = 1.85 \times 10^{-3} \text{ S cm}^{-1}$) represents a **16.8-fold improvement** over undoped batch NRI-2024-0041 ($\sigma = 1.10 \times 10^{-4} \text{ S cm}^{-1}$) and surpasses the $3.0 \times 10^{-4} \text{ S cm}^{-1}$ hypothesis threshold by a factor of 6.2. This result aligns with literature values for Al-doped cubic LLZO [1, 2] and confirms efficient phase stabilisation.

Grain boundary resistance

The grain-boundary contribution ($R_{gb} = 312.7 \text{ } \Omega$) accounts for 67.8 % of total impedance, indicating grain-boundary resistance as the dominant limitation. This is higher than the 55 % reported in [1]

for similar compositions, suggesting further optimisation of sintering temperature or dwell time may be beneficial. A companion experiment at 1175 °C is planned for batch NRI-2024-0050.

Relative density shortfall

Relative density of 92.8 % falls below the 94 % target. Possible causes:

- Use of furnace NRI-F-02 (deviation) — thermocouple calibrated but temperature profile across sample zone may differ from NRI-F-01.
- Insufficient milling homogeneity following jar replacement in Step 3 (milling jar changeover interrupted the programmed milling cycle by ~18 min).

Despite the density shortfall, ionic conductivity substantially exceeds the target, suggesting that grain-boundary chemistry (Al segregation) dominates over microstructural porosity in this composition window.

Key Findings

- ✓ Cubic LLZO phase confirmed.
- ✓ $\sigma = 1.85 \times 10^{-3} \text{ S cm}^{-1}$.
- ✓ Hypothesis exceeded by $\times 6.2$.
- ✗ Relative density below target (92.8 %).
- ✗ Pellet P-047-B cracked during pressing.

Next Steps

- Rietveld refinement (P. Nair, 16 Nov).
- 0.4 mol% Al batch (NRI-2024-0048).
- SEM cross-section of P-047-A.
- Repeat with NRI-F-01 once available.
- Update project tracking in Synapse LIMS.

References

- [1] Charles A. Geiger, Evgeny Alekseev, Biljana Lazic, Martin Fisch, Thomas Armbruster, Reinhard Langner, Michael Fechtelkord, Nojiri Kim, Thomas Pettke, and Werner Weppner. Crystal chemistry and stability of “ $\text{Li}_7\text{La}_3\text{Zr}_2\text{O}_{12}$ ” garnet: A fast lithium-ion conductor. *Inorganic Chemistry*, 50(4):1089–1097, 2011.
- [2] Ramaswamy Murugan, Venkataraman Thangadurai, and Werner Weppner. Fast lithium ion conduction in garnet-type $\text{Li}_7\text{La}_3\text{Zr}_2\text{O}_{12}$. *Angewandte Chemie International Edition*, 46(41):7778–7781, 2007.

 Entry Sign-Off & Witnessing

I hereby certify that the experimental work, observations, and data recorded in this notebook entry (Experiment ID: **NRI-2024-0047**, date: **14 November 2024**) are accurate and a true record of work conducted in accordance with Nexa Research Institute quality and safety standards.

James Okonkwo
Research Associate II
Nexa Research Institute

Dr. Elena Marchetti
Principal Investigator (Witness)
Nexa Research Institute

Entry completed:
14 November 2024, 20:15

Witnessed:
15 November 2024, 09:03

Next entry:
NRI-2024-0048

 **LIMS Record:** NRI-LIMS-2024-0047

 **Barcode:** NRI0047-2024-1114

 Synapse LIMS v3.4